



FILAVA

FILAVA™ is a direct roving made of enhanced volcanic rock filaments and manufactured in the melt spinning process, where the fibers are formed via a batch melt, followed by the lava which flows through bushing plates with nozzles and then vitrified by cooling.

FILAVA™ roving is a unique product thanks to a genuine and innovative treatment of the raw material, basalt, which being the major ingredient, is enriched with various mineral additives with the aim to increase and guarantee its original mechanical and chemical properties. The components used in the batch aggregation and the fabrication process are ISOMATEX's know-how and constitute its exclusive expertise.

Single-End and Multi-End assembly direct rovings consist of thousands of continuous filaments with elementary diameters from 9,0 to 11,0 µm. bonded into a single strand and wound onto a cardboard sleeves. A specially developed by matrices' type sizing is applied on the fibers, which assures an excellent infusion and resin-to-reinforcement adhesion.

FILAVA™ is unique due to its **high strength, high elasticity and resistance to high temperature as well as to temperature's variation** (contrarily to carbon which does not like thermal shocks). This compares well to existing high-end products (R - glassfibers, S - glassfibers). In addition and as noted above **FILAVA™** is always better in a chemical and alkaline environment, which gives it often a definitive advantage (for instance water and concrete is alkaline, which makes other high-end products not so suitable whenever the fiber is in contact with such elements).

Applications and downstream processing. **FILAVA™** rovings are designed to be used in applications requiring high mechanical properties, well wet-out and high infusion with organic matrices, where excellent processing is necessary, in thermoset matrices like epoxy resin, polyester, vinyl ester as well as in many thermoplastic systems. **FILAVA™** has very low catenary with smooth unwinding behavior throughout the package and has low fuzz properties that will result in smoother parts, less clean-up and improved machine efficiencies in downstream processing. Typical applications include weaving, braiding, high speed knitting, filament winding, UD-impregnation and pultrusion, **chopping, ...etc.**

High mechanical properties such as Tensile Strength and Young modulus (elasticity), elongation and resistance to high temperature, chemical and alkali-resistance offers a unique combination of properties making **FILAVA™** completely compliant to the technical requirements of such high-end applications.

The applications where **FILAVA™** is used are basically endless ...

Packaging. Standard packaging includes cylindrical bobbins with felt- or embossed surface sleeves. The inner diameter of cardboard sleeves is 76,0 mm., the height: 260 ... 300 mm. Bobbins are individually labelled and wrapped with stretched plastic film for protection and improved handling. Nominal weight for commercially available bobbins is in range of 5,0 up to 7,5 kg.

Storage and usage conditions. ISOMATEX recommends storage in a cool and dry warehouse into the original packaging. For an optimal processing we recommend to use the product in ambient conditions (20 - 23 °C, 60 - 65% Relative Humidity).

FILAVA™ roving need to be kept in the workshop at least 24 hours prior usage.

Chemical resistance (Weight loss % after boiling during 3 h):

• H ₂ O:	0,51 0,7 %
• 2N NaOH:	4,65 %
• 2N HCl:	3,53 %

Thermal resistance (% of residual values (after 24 h ageing):

• - 200 °C:	100%
• 200 °C:	100%
• 850°C:	40%

DISCLAIMER OF LIABILITY

The above shown data is presented solely as a guide in the selection of a fiber reinforcement. The information mentioned in this leaflet is based on actual ISOMATEX laboratory data and field test experience. Because of numerous factors in downstream processability affecting results, we consider this information to be reliable, but do not guarantee its applicability to the user's process or assume any liability arising out of its use or performance. The end-user, by accepting the products described herein, assume the responsibility for thoroughly testing any application to determine its compliance before committing to production. It is important for the end-user to determine the properties of its own commercial compounds when using this or any other fiber reinforcement.

WE MAKE NO WARRANTY OF ANY KIND, EXPRESS OR IMPLIED, INCLUDING THOSE OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. STATEMENTS AND DATA IN THIS DOCUMENT SHALL NOT BE UNDERSTOOD AS REPRESENTATIONS OR WARRANTIES OR AS INDUCEMENTS TO INFRINGE ANY PATENT OR VIOLATE ANY LAW, SAFETY CODE, OR INSURANCE REGULATION.